



FURRER
CARRARA

AVORIO



DATA SHEET


- ULTIMATE TENSILE STRENGTH [UTS] TO PRESSURE	kg/cm ²	89,4
- ULTIMATE TENSILE STRENGTH [UTS] AFTER FREEZING CYCLES	kg/cm ²	2110
- ULTIMATE TENSILE STRENGTH [UTS] TO BENDING STRESS	kg/cm ²	20,1
- THERMIC LINEAR DILATATION	mm/m°C	16
- WATER ABSORPTION COEFFICIENT	%	0,12
- IMPACT STRENGTH	cm	0,3
- ABRASION STRENGTH	mm	43
- WEIGHT PER UNIT VOLUME	KG/m ³	2710

SHOW ROOM
Via Covetta, 1
54033 Avenza, Carrara

HEADQUARTER
Via Covetta, 2
54030 Carrara (MS) Italy



FURRER
CARRARA



SHOW ROOM
Via Covetta, 1
54033 Avenza, Carrara

HEADQUARTER
Via Covetta, 2
54030 Carrara (MS) Italy