




**FURRER**  
CARRARA

## BIANCO ACQUABIANCA



### DATA SHEET

- ULTIMATE TENSILE STRENGTH [UTS] TO PRESSURE	kg/cm <sup>2</sup>	103,5
- ULTIMATE TENSILE STRENGTH [UTS] AFTER FREEZING CYCLES	kg/cm <sup>2</sup>	1260
- ULTIMATE TENSILE STRENGTH [UTS] TO BENDING STRESS	kg/cm <sup>2</sup>	7,9
- THERMIC LINEAR DILATATION	mm/m°C	26
- WATER ABSORPTION COEFFICIENT	%	0,19
- IMPACT STRENGTH	cm	0,4
- ABRASION STRENGTH	mm	57
- WEIGHT PER UNIT VOLUME	KG/m <sup>3</sup>	2700

**SHOW ROOM**  
Via Covetta, 1  
54033 Avenza, Carrara

**HEADQUARTER**  
Via Covetta, 2  
54030 Carrara (MS) Italy



**FURRER**  
CARRARA



**SHOW ROOM**  
Via Covetta, 1  
54033 Avenza, Carrara

**HEADQUARTER**  
Via Covetta, 2  
54030 Carrara (MS) Italy